

## Glass Outlet Set-Fast Grout

### PROPERTIES

- Aggregate free
- Rapid strength gain facilitates for rapid installation
- Ready to use, pre-mixed, requires only the addition of water
- Can be mixed for stiff, plastic, flowable or fluid application
- Lower water/cement ratio reduces drying shrinkage, increases durability and reduces permeability
- Dual expansion compensates for shrinkage in the plastic and hardened state

### RECOMMENDED USES

- Spigot and channel fixing
- Cementitious grouting where particular application requires rapid setting
- Anchoring bolts, bars and fittings

### MIXING

Add water to a clean bucket (3ltrs to 1 x 10kg bag) mix ratio 30% water to 1kg (think pancake like consistency). More water can be added to achieve a more flowable consistency. More than 40% water not advisable. Start mixing using an electric mixing paddle (preferably using a paddle mixing blade) while the powder is slowly added. Once all of the powder is added, mix on medium speed for 30 seconds then scrape the sides of the bucket to make sure all of the powder is properly dissolved. Mix for another 60 seconds. Use immediately.

### SET TIMES

Glass Outlet Set-Fast Grout has varying factors that effect the set time. All guides are estimated times only. Factors to consider when using; air temperature, water temperature, water volume, powder temperature and amount being mixed (larger amounts mixed will speed up the set time). Set times below are based on air, water and powder temperature at 22 deg and the volume being mixed is 5kg

- 10° Degrees 30 - 40 Mins
- 25° Degrees 10 - 15 Mins
- 35° Degrees and above less than 10 Mins

### HIGH TEMPERATURE WORKING

At temperatures above 30°C, it is advisable to use water below 20°C when mixing grout. All materials must be kept cool and away from direct sunlight. If practical, the installation area should be shaded by erecting shade screens. If ambient temperatures are excessive, grouting should be scheduled for early morning or late afternoon.

### LOW TEMPERATURE WORKING

At temperatures below 5°C the cure rate and strength development rate will be dramatically reduced. If early strength is required, it is advisable to use heated water to 25°C. Do not exceed this temperature.

### CLEAN- UP

Glass Outlet Set-Fast Grout should be removed from tools and equipment with clean water immediately after use.

### STORAGE & SHELF LIFE

12 months when stored in the original unopened packaging, in a dry place at 23°C and 50% relative humidity.

**WARNING:** Glass Outlet Set-Fast Grout has very strong expansion properties which generate the high tensile loads that can be achieved. We do not recommend its use in hollow bricks, concrete block, limestone or granite. Always leave at least 100mm from the edge of the concrete to the hole